



## TECHNICAL DATA SHEET

# RIV-306

**DESCRIPTION :** This product was formulated for multiples usages. It will give a permanent bond. HOT MELT. Heat seal. conventional equipment application. This product develops an aggressive wet tack very quickly. This is a premium product for difficult carton stock. Softening point:( 225 F-107 C )  
Application temperature : 177°C (350°F).

### PROPERTIES :

BASE	General polymer. (Polymer.)
COLOR	Yellowish. Molten adhesive is transparent. (Light.)
VISCOSITY (cP at 177°C/350°F)	650-950
VISCOSITY (cP at 150°C/300°F)	0% (v/v). 0% (w/w).
SOFTING POINT (°C)	100 to 110°C (212 to 230°F)
TOXICITY	Not controlled under WHMIS (Canada).
SPECIFIC GRAVITY	0.98 (Water = 1)
STORAGE LIFE (MONTH)	12
CLEAN UP/DILUENT	pot cleaning (39069)
FILM PROPERTIES	Flexible
F.D.A.	Oui-yes 175.105
REVISION DATE	2004-09-10

**NON-WARRANTY-** The facts stated and the recommendations made with respect to the use of any product are based on our own experiences and/or the experiences of others, and are believed to be reliable. However no garrantee of their accuracy is made. Before the using, purchaser shall determine the suitability of the product for his intended use, and purchaser assumes all risk and liability for loss, damage or expense directly or indirectly arising from the handling of use of the material or from any other cause whatever.

**NON-GARANTIE-** Les faits établis et les recommandations relatifs à l'utilisation de tout produit sont basés sur nos propres expériences et/ou sur les expériences de tierces personnes et celles-ci sont réputés être sûre. Toutefois, aucune garantie n'est accordée quand à leur exactitude. Avant l'utilisation, l'acheteur devra déterminer si le produit convient à l'utilisation qu'il entend en faire et l'acheteur assume tous les risques et toutes les responsabilités quant aux pertes, dommages ou dépenses causés directement ou indirectement par la manipulation ou l'utilisation du matériel ou par toute autre cause que ce soit.

Adhpro Adhesives Inc.  
1650, Industriel Boul.  
Magog, Quebec J1X 4V9  
Tel: (819) 847-2269  
Fax:(819) 847-4990

Adhpro Adhesives Maritimes Inc.  
Dartmouth, Nova Scotia, B2W 4Y3  
Tel.: (902) 468-4583  
Fax: (902) 468-4332

Adhpro Adhesives inc.  
Toronto, Ontario  
Tel.: (877) 245-2054  
Fax: (877) 245-2053

[www.adhpro.com](http://www.adhpro.com)