



## TECHNICAL DATA SHEET

# RIV-327

**DESCRIPTION :** This product was formulated for multiples usages. It will give a permanent bond. HOT MELT. Heat seal. conventional equipment application. This product develops an aggressive wet tack very quickly. This is a premium product for difficult carton stock. Softening point:( 225 F-107 C )

**PROPERTIES :**

BASE	Polymer.
COLOR	Amber. [Light]
VISCOSITY (cP at 177°C/350°F)	900-( 350 F-177 C ) Rapide
VISCOSITY (cP at 150°C/300°F)	Not available.
SOFTING POINT (°C)	107.22°C (225°F)
SPECIFIC GRAVITY	0.98
STORAGE LIFE (MONTH)	12
CLEAN UP/DILUENT	81015-01
FILM PROPERTIES	Flexible
F.D.A.	Oui-yes 175.105
REVISION DATE	2009-05-07

**NON-WARRANTY-** The facts stated and the recommendations made with respect to the use of any product are based on our own experiences and/or the experiences of others, and are believed to be reliable. However no garrantee of their accuracy is made. Before the using, purchaser shall determine the suitability of the product for his intended use, and purchaser assumes all risk and liability for loss, damage or expense directly or indirectly arising from the handling of use of the material or from any other cause whatever.

**NON-GARANTIE-** Les faits établis et les recommandations relatifs à l'utilisation de tout produit sont basés sur nos propres expériences et/ou sur les expériences de tierces personnes et celles-ci sont réputés être sûre. Toutefois, aucune garantie n'est accordée quand à leur exactitude. Avant l'utilisation, l'acheteur devra déterminer si le produit convient à l'utilisation qu'il entend en faire et l'acheteur assume tous les risques et toutes les responsabilités quant aux pertes, dommages ou dépenses causés directement ou indirectement par la manipulation ou l'utilisation du matériel ou par toute autre cause que ce soit.

## ADHPRO ADHESIVES INC.

1650, Industriel Boul.  
Magog, **Quebec** J1X 4V9  
Tel: (819) 847-2269  
Fax:(819) 847-4990

Dartmouth, **Nova Scotia**  
Tel.: (877) 245-2054  
Fax: (877) 245-2053

Whitby, **Ontario**  
Tel.: (877) 245-2054  
Fax: (877) 245-2053

[WWW.ADHPRO.COM](http://WWW.ADHPRO.COM)